

BEST AVAILABLE COPY JAN 29 2007

Application No.: 10/017268

Case No.: 57013US002

AMENDMENTS TO THE CLAIMS

Please add claims 52-56.

Please amend claim 1 as follows.

The following Listing of Claims will replace all prior versions and listings of claims in the application:

Listing of Claims

1. (Currently Amended) A method for making a touch activated user input device comprising:
 - providing a first substrate comprising a first conductive coating;
 - ink jet printing a plurality of dots on the first conductive, each of the dots including nanoparticles;
 - hardening the dots to form spacers adhered to the first substrate; and
 - placing a second substrate comprising a second conductive coating over the first substrate such that the spacers maintain a distance between the first and second substrates to prevent detection of a touch location when no external force is applied and allow detection of a localized touch location when a sufficient localized external force is applied between the first and second substrates.
2. (Original) The method of claim 1, wherein the dots comprise a nanocomposite comprising surface-modified inorganic nanoparticles.
3. (Original) The method of claim 2, wherein the surface-modified inorganic nanoparticles include silica nanoparticles.
4. (Original) The method of claim 2, wherein the nanoparticles are present in an amount of about 5% or more by weight of the nanocomposite.

Application No.: 10/017268

Case No.: 57013US002

5. (Original) The method of claim 2, wherein the nanoparticles are present in an amount of about 10% to 40% by weight of the nanocomposite.
6. (Original) The method of claim 2, wherein the nanoparticles have an average diameter in a range of about 10 to 30 nm.
7. (Original) The method of claim 2, wherein the nanocomposite further comprises hexanediol diacrylate.
8. (Original) The method of claim 1, wherein the step of ink jet printing a plurality of dots comprises ink jet printing a heated gel composition.
9. (Original) The method of claim 8, wherein the gel composition comprises a nanocomposite gel.
10. (Original) The method of claim 9, wherein the nanocomposite gel composition comprises surface-modified silica nanoparticles dispersed in an energy curable fluid vehicle.
11. (Original) The method of claim 10, wherein the energy curable fluid vehicle comprises hexanediol diacrylate.
12. (Original) The method of claim 10, wherein the silica nanoparticles are present in an amount of about 5% or more by weight of the nanocomposite gel.
13. (Original) The method of claim 10, wherein the silica nanoparticles are present in an amount of about 10% to 40% by weight of the nanocomposite gel.
14. (Original) The method of claim 10, wherein the silica nanoparticles have an average diameter of about 10 to 30 nm.

Application No.: 10/017268

Case No.: 57013US002

15. (Original) The method of claim 1, wherein the first and second conductive coatings each comprise a transparent conductive coating.
16. (Original) The method of claim 1, wherein the spacer dots have heights of about 2 microns or more and have height to diameter aspect ratios of about 1:10 or more.
17. (Original) The method of claim 1, wherein the step of ink jet printing comprises ink jet printing a material onto a pre-existing dot.
18. (Original) The method of claim 1, further comprising associating the touch activated user input device with an electronic display.
19. (Withdrawn) A method for forming dots suitable as spacers in touch panels, which method comprises the steps of:
- providing curable gel composition;
 - heating the gel composition to form a liquid composition;
 - ink jetting the liquid composition onto a transparent conductive coating to form a plurality of dots;
 - cooling the dots into a gel state; and
 - curing the dots to adhere the dots to the transparent conductive coating,
- wherein the cured dots have heights of about 2 microns or more, and have height to diameter aspect ratios of about 1:10 or more.
20. (Withdrawn) The method of claim 0, wherein the curable gel composition comprises a nanocomposite.
21. (Withdrawn) The method of claim 20, wherein the nanocomposite comprises silica nanoparticles dispersed in a binder material.
22. (Withdrawn) The method of claim 21, wherein the binder material comprises an acrylate material.

Application No.: 10/017268

Case No.: 57013US002

22. (Withdrawn) The method of claim 0, wherein the transparent conductive coating comprises indium tin oxide.
24. (Withdrawn) A method for making touch panel spacer dots comprising:
printing a nanocomposite composition comprising surface-modified inorganic nanoparticles dispersed in an energy curable fluid vehicle to form a plurality of curable dots on a conductive coating; and
curing the curable dots to adhere the dots to the conductive coating.
25. (Withdrawn) The method of claim 24, wherein the step of printing the nanocomposite composition comprises ink jet printing.
26. (Withdrawn) The method of claim 25, wherein ink jet printing comprises heating the composition, ink jetting the heated composition, and cooling the ink jetted composition to form the plurality of curable dots.
27. (Withdrawn) The method of claim 24, wherein the step of printing the nanocomposite composition comprises screen printing.
28. (Withdrawn) The method of claim 24, wherein the nanocomposite composition comprises a nanocomposite gel composition.
29. (Withdrawn) The method of claim 24, wherein the nanocomposite composition comprises silica nanoparticles.
30. (Withdrawn) The method of claim 24, wherein the nanoparticles are present in an amount of about 5% or more by weight of the nanocomposite composition.
31. (Withdrawn) The method of claim 24, wherein the nanoparticles are present in an amount of about 10% to 40% by weight of the nanocomposite composition.

Application No.: 10/017268

Case No.: 57013US002

32. (Withdrawn) The method of claim 24, wherein the nanoparticles have an average size of about 10 to 30 nm.

33. (Withdrawn) The method of claim 24, wherein the nanocomposite further comprises hexanediol diacrylate.

34. (Withdrawn) The method of claim 24, wherein the conductive coating comprises a transparent conductive oxide.

35. (Withdrawn) The method of claim 34, wherein the transparent conductive oxide comprises indium tin oxide.

36. (Withdrawn) A method of making touch panel spacer dots comprising:
selecting a transparent conductive coating suitable for use in a touch panel;
formulating a curable gel composition capable of (i) being ink jet printed onto the transparent conductive coating to form a droplet on the transparent conductive coating that has a height to diameter aspect ratio of about 1:10 or more for droplets having height of about 2 to 10 microns or more, and (ii) adhering to the transparent conductive coating upon curing, without modifications to the transparent conductive coating.

37. (Withdrawn) The method of claim 36, wherein the curable gel composition comprises a nanocomposite gel composition.

38. (Withdrawn) The method of claim 37, wherein the nanocomposite gel composition comprises surface-modified silica nanoparticles dispersed in a binder.

39. (Withdrawn) The method of claim 38, wherein the binder comprises an acrylate material.

Application No.: 10/017268

Case No.: 57013US002

40. (Withdrawn) The method of claim 38, wherein the silica nanoparticles are present in an amount of about 5% or more by weight of the nanocomposite gel.

41. (Withdrawn) The method of claim 38, wherein the silica nanoparticles are present in an amount of about 10% to 40% by weight of the nanocomposite gel.

42. (Withdrawn) The method of claim 38, wherein the silica nanoparticles have average diameters of about 10 to 30 nm.

43. (Withdrawn) The method of claim 36, wherein selecting a transparent conductive coating comprises selecting an indium tin oxide coating.

44. (Cancelled) A touch panel comprising:
a first substrate comprising a first conductive coating;
a second substrate comprising a second conductive coating; and
a plurality of spacer dots disposed between the first and second substrates to maintain a distance between the first and second substrates to prevent detection of a touch location when no external force is applied and allow detection of a localized touch location when a sufficient localized external force is applied between the first and second substrates,
wherein the plurality of spacers dots comprise a nanocomposite material comprising about 5% or more by weight of surface-modified inorganic nanoparticles.

45. (Cancelled) The touch panel of claim 44, wherein the nanocomposite material comprises about 10% to 40% by weight of surface-modified inorganic nanoparticles.

46. (Cancelled) The touch panel of claim 44, wherein the surface-modified inorganic nanoparticles comprise silica particles.

47. (Cancelled) The touch panel of claim 44, wherein the nanocomposite further comprises an acrylate material.

Application No.: 10/017268

Case No.: 57013US002

48. (Cancelled) The touch panel of claim 44, wherein at least one of the first and second conductive coatings comprises a transparent conductive coating.

49. (Withdrawn) A method for making touch panel spacer dots comprising:
providing a touch panel substrate comprising a plurality of spacer dots;
inspecting the substrate for missing or damaged spacer dots; and
ink jet printing material to fill in or repair a missing or damaged spacer dot identified in the inspecting step.

50. (Cancelled) A display system comprising a touch panel comprising:
a first substrate;
a second substrate disposed over the first substrate; and
a plurality of spacer dots disposed between the first and second substrates,
wherein said spacer dots are formed by ink jet printing.

51. (Cancelled) A display system comprising a touch panel comprising:
a first substrate;
a second substrate disposed over the first substrate; and
a plurality of spacer dots comprising a nanocomposite material including about
5% or more by weight of surface-modified inorganic nanoparticles.

52. (New) A method for making a touch activated user input device comprising:
providing a first substrate comprising a first conductive coating;
ink jet printing a gel composition to define a plurality of dots on the first conductive coating;
hardening the dots to form spacers adhered to the first substrate; and
placing a second substrate comprising a second conductive coating over the first
substrate such that the spacers maintain a distance between the first and second substrates to
prevent detection of a touch location when no external force is applied and allow detection of a
localized touch location when a sufficient localized external force is applied between the first and
second substrates.

Application No.: 10/017268

Case No.: 57013US002

53. (New) The method of claim 52, wherein the gel composition comprises a nanocomposite gel including nanoparticles dispersed in an energy curable fluid vehicle.

54. (New) The method of claim 53, wherein the nanoparticles comprises surface-modified silica nanoparticles.

55. (New) The method of claim 53, wherein the nanoparticles have an average diameter in a range of about 10 to 30 nm.

56. (New) The method of claim 52, wherein the gel composition comprises hexanediol diacrylate.

**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ **BLACK BORDERS**
- ☐ **IMAGE CUT OFF AT TOP, BOTTOM OR SIDES**
- ☐ **FADED TEXT OR DRAWING**
- ☐ **BLURRED OR ILLEGIBLE TEXT OR DRAWING**
- ☐ **SKEWED/SLANTED IMAGES**
- ☐ **COLOR OR BLACK AND WHITE PHOTOGRAPHS**
- ☐ **GRAY SCALE DOCUMENTS**
- ☒ **LINES OR MARKS ON ORIGINAL DOCUMENT**
- ☐ **REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY**
- ☐ **OTHER:** _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.